




NATIVIA[®] NBSS

**BoPLA transparent film, both sides
heat sealable, for metallising,
biodegradable**



ENVIRONMENTAL

- Made from annually renewable source
- Biodegradable into carbon dioxide, water and biomass by microbial digestion
- Certified DIN EN 13432 (7H0051) for Compostable intermediates.

This logo can be used for final products which are made of this intermediate and certified with a 7P-number as final products at DIN CERTCO.



- Certified TÜV AUSTRIA (four-star certification) OK biobased (S206)



PROPERTIES

- For metallising and/or coating on treated side
- Heat sealable on both sides
- Good mechanical properties
- High stiffness
- Good oxygen barrier
- Excellent moisture transmission
- Resistant to oil, fat and alcohol
- Excellent twist retention

TYPICAL APPLICATIONS

- Specifically formulated for metallising and coating

ROLL SIZE AVAILABILITY*

Film	Standard Length (m)	4x ** (m)	7x (m)
NATIVIA [®] NBSS 20	3,200	12,800	22,400
NATIVIA [®] NBSS 25	2,550	10,200	17,850
NATIVIA [®] NBSS 30	2,100	8,400	14,700
NATIVIA [®] NBSS 40	1,600	6,400	11,200
Outside diameter – core 76 mm	305 mm	588 mm	
Outside diameter - core 152 mm	337 mm	605 mm	783 mm

*Regional availability of roll sizes (multiples of standard length)-please refer to the corresponding Sales Representative

**Length rolls on 152 mm cores will be produced with reduced length in Europe to maintain roll diameters below 600 mm

NATIVIA[®] NBSS

Properties	Method	Unit	Ref.	Typical values			
Nominal thickness	Internal method	µm		20	25	30	40
Unit weight		g/m ²		24.8	31.0	37.2	49.6
Yield		m ² /kg		40.3	32.3	26.9	20.2
Tensile strength	ASTM D882	N/mm ²	MD TD	105 205			
Elongation at break		%	MD TD	185 85			
Dynamic COF	ASTM D1894		NT/NT	0.35			
Haze	ASTM D1003	%		1.5			1.8
Gloss (45°)	ASTM D2457	Gloss Unit		80			
Heat seal range	Internal method	°C		85 - 140			
Seal strength	Internal method 85°C ;0.5 s	g/cm		230	290	350	
Treatment Level	ASTM D2578	mN/m		43	45		
Water vapour permeability	ASTM F1249 (38°C - 90% RH)	g/m ² /d		440	330	270	200
Oxygen permeability	ASTMD3985 (23°C - 0% RH)	cm ³ /m ² /d		1100	900	730	540

Order volume tolerance

	≤ 1.000 kg	± 20%
Weight	1.001-10.000 kg	± 10%
	> 10.000 kg	± 5%

PRINTABILITY/LAMINATION

NATIVIA[®] can be converted on flexo- and rotogravure print presses. In comparison to other polyolefin substrates, it needs rather low drying temperatures and a high airflow for best print results. Any solvent, except Ethyl Acetate, can be used. Ethyl Acetate will cause swelling effects up to total disintegration of the PLA.

It is important to contact your ink and/or adhesive supplier for best choice of products. Appropriated tests should be carried out before converting.

STORAGE, HANDLING AND APPLICATION

NATIVIA[®] NBSS does not require special storage conditions. A storage temperature below 30°C is needed in order to minimise the deterioration of the film properties in general. It is advisable to turn over the inventory according to the delivery date (first in - first out). The film should be conditioned in the operating environment at least for 24 hours before processing. NATIVIA[®] NBSS is suitable for use up to 6 months from the date of production, if properly stored.

INDICATION OF SURFACE TREATMENT

NATIVIA[®] NBSS is supplied with corona treatment on the outside surface (TO).

FOOD CONTACT

NATIVIA[®] NBSS complies with EU and FDA regulations. Specific documents and MSDS are available on request.

The property values represented in the table do not constitute product specifications, but represent the average or typical values. Use of this information is limited to the specific recipient. While the information is accurate to the best of our knowledge as of the date compiled, it is limited to the information as specified. No representation or warranty, expressed or implied, is made regarding the information, or its completeness or fitness to a particular use. The user is solely responsible for all determinations regarding use and we disclaim liability for any loss or damage that may occur from the use of this information. *Ti* does not guarantee the typical (or other) values.